

Quick Mixing Reference Primers

Product code	Product name	Content Binder/Toner	Mixing ratio	Activator	Reducer	Mixing stick
FP300	Synthetic Primer DTM Grey (only Reducer)	---	100 + 15-30%	---	RS300 15-30%	
FP300	Synthetic Primer DTM Grey (with Activator)	---	4 : 1 + 0-10%	AS300 max.25%	RS300 0-10%	M2 74-202
PB300	Synthetic Primer DTM Tintable (only Reducer)	80 / 20	100 + 15-30%	---	RS300 15-30%	
PB300	Synthetic Primer DTM Tintable (with Activator)	80 / 20	4 : 1 + 0-10%	AS300 max.25%	RS300 0-10%	M2 74-202
FP400	Epoxy Primer DTM Grey (sanding)	---	3 : 1	AP401	RS605*	M2
FP401	Epoxy Primer DTM White	---	+ 10-30%	3:1	10-30%	74-202
FP400	Epoxy Primer DTM Grey (non-sanding)	---	3 : 1	AP401	RS605*	M2
FP401	Epoxy Primer DTM White	---	+ 10-30%	3:1	35-50%	74-202
FP402	Epoxy Primer Zinc Rich (by weight)	---	1000 gr.	AP402 82,5 gr.	RS605* 25-60 gr.	
FP500	PU Primer DTM Grey	---	8 : 1 + 10-25%	AU500 8:1	RS605* 10-25%	M5 74-205
PB500	PU Primer DTM Tintable	80 / 20	8 : 1 + 10-25%	AU500 8:1	RS605* 10-25%	M5 74-205